

Polymist® XPP 552V

PTFE

Syensqo

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	325	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Bulk Density	325	kg/m ³	-

Characteristics**Processing**

Coating

Delivery form

Powder, White

Additives

Antiblocking agent

Special Characteristics

Heat stabilized or stable to heat

Chemical Resistance

General Chemical Resistance

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa