

RULON® LR

PTFE

Saint-Gobain Performance Plastics

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	13.8	MPa	ASTM D 638

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Coefficient of Thermal Expansion, MD	63	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	112	E-6/K	ASTM D 696

Other properties	Value	Unit	Test Standard
Density	2250	kg/m ³	ASTM D 792

Characteristics**Processing**

Other Extrusion

Special Characteristics

Flame retardant

Features

Creep Resistance

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific, South and Central America