

RULON® XL

PTFE

Saint-Gobain Performance Plastics

| Mechanical properties | Value | Unit | Test Standard |
|--------------------------------------|--------------|-------------------|----------------------|
| ASTM Data | | | |
| Tensile Strength | 11.7 | MPa | ASTM D 638 |
| Thermal properties | | | |
| ASTM Data | | | |
| Coefficient of Thermal Expansion, TD | 115 | E-6/K | ASTM D 696 |
| Other properties | | | |
| Density | 1970 | kg/m ³ | ASTM D 792 |

Characteristics**Processing**

Other Extrusion

Special Characteristics

Flame retardant

Features

Tribologic Grade

Chemical Resistance

General Chemical Resistance

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific, South and Central America