

Mechanical properties	Value	Unit	Test Standard
Other Standards^{S1}			
Tensile Strength	48.3	MPa	ASTM D 4894
Elongation at Break	375	%	ASTM D 4894

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Moisture Content	0.04	%	-
Bulk Density	460	kg/m ³	-
Other Standards^{S1}			
Density	2160	kg/m ³	ASTM D 4894

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics

Delivery form

Powder, White

Special Characteristics

U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Features

Tribologic Grade

Chemical Resistance

General Chemical Resistance

Certifications

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America