

Mechanical properties	Value	Unit	Test Standard
Other Standards^{S1}			
Tensile Strength	41.4	MPa	ASTM D 4894
Elongation at Break	330	%	ASTM D 4894

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Moisture Content	0.04	%	-
Bulk Density	680	kg/m ³	-
Other Standards^{S1}			
Density	2150	kg/m ³	ASTM D 4894

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics

Processing

Pipe/Tube Extrusion, Other Extrusion

Delivery form

Powder, White

Special Characteristics

U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Features

Tribologic Grade

Chemical Resistance

General Chemical Resistance

Certifications

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

Regional Availability

North America, Europe, Asia Pacific, South and Central America