

# Teflon™ PTFE 62 X

PTFE

The Chemours Company

Thermal properties	Value	Unit	Test Standard
<b>Other Standards<sup>S1</sup></b>			
Max. Service Temp., Intermittent	260	°C	-

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Bulk Density	495	kg/m <sup>3</sup>	-
<b>Other Standards<sup>S1</sup></b>			
Density	2150	kg/m <sup>3</sup>	ASTM D 4895

S: These properties are reported by the producer according standards that are different to our defaults.

## Characteristics

### Processing

Pipe/Tube Extrusion, Other Extrusion, Coating, Blow Molding

### Delivery form

Powder

### Special Characteristics

U.V. stabilized or stable to weather

### Features

Thermal Stability, Tribologic Grade

### Chemical Resistance

General Chemical Resistance, Environmental Stress Crack Resistance, Solvent Resistance

### Certifications

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

### Applications

Automotive

### Regional Availability

North America, Europe, Asia Pacific, South and Central America