

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>Other Standards<sup>S1</sup></b>			
Tensile Strength	<b>33</b>	MPa	ASTM D 4894
Elongation at Break	<b>320</b>	%	ASTM D 4894

S: These properties are reported by the producer according standards that are different to our defaults.

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Moisture Content	<b>0.04</b>	%	-
Bulk Density	<b>900</b>	kg/m <sup>3</sup>	-
<b>Other Standards<sup>S1</sup></b>			
Density	<b>2160</b>	kg/m <sup>3</sup>	ASTM D 4894

S: These properties are reported by the producer according standards that are different to our defaults.

**Characteristics**

**Processing**

Other Extrusion, Compression Molding

**Delivery form**

Granules

**Special Characteristics**

U.V. stabilized or stable to weather, Heat stabilized or stable to heat

**Features**

Tribologic Grade

**Chemical Resistance**

General Chemical Resistance

**Certifications**

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

**Applications**

Electrical and Electronical

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America