

Mechanical properties	Value	Unit	Test Standard
Other Standards^[S]			
Tensile Strength	41.4	MPa	ASTM D 4894
Elongation at Break	600	%	ASTM D 4894

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Bulk Density	400	kg/m ³	-
Other Standards^[S]			
Density	2170	kg/m ³	ASTM D 4894

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics

Processing

Compression Molding

Special Characteristics

U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Features

Tribologic Grade, Weldable

Chemical Resistance

General Chemical Resistance

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

North America, Europe, Asia Pacific, South and Central America