

Mechanical properties	Value	Unit	Test Standard
Other Standards^[S]			
Tensile Strength	27.6	MPa	ASTM D 4894
Elongation at Break	450	%	ASTM D 4894

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Bulk Density	700	kg/m ³	-
Other Standards^[S]			
Density	2170	kg/m ³	ASTM D 4894

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics

Processing

Other Extrusion

Delivery form

Pellets

Special Characteristics

U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Features

Tribologic Grade, Weldable

Chemical Resistance

General Chemical Resistance

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America