

Helios Support

PVAL

Formfutura BV

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	58	g/10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-
Other properties			
Density	1190	kg/m ³	ISO 1183

Characteristics

Processing

Additive Manufacturing

Regional Availability

Europe

Delivery form

Monofilament