

113B-FR

PVC, Flexible

Westlake Chemical Corp.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	16.5	MPa	ASTM D 638
Shore A Hardness	90	-	ASTM D 2240

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-1	-	UL 94
Thickness tested	0.508	mm	-
Limiting Oxygen Index	24	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1250	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

North America