

2222C-78 CLEAR 0003

PVC, Flexible

Alphagary

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	21	MPa	ASTM D 638
Elongation at Break	375	%	ASTM D 638
Shore A Hardness	76	-	ASTM D 2240
Other Standards^[S]			
Modulus at 100% Elongation	9.38	MPa	ASTM D 638

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	1220	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

Transparent

Applications

Medical

Features

Low Gel, Thermal Stability

Regional Availability

North America, Europe

Certifications

Food contact, Food approval FDA 21 CFR