

**2235L-80 CLEAR 030X**

PVC, Flexible

Alphagary

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>0.4</b>	g/10min	ASTM D 1238
Temperature	<b>175</b>	°C	-
Load	<b>20</b>	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength	<b>19.7</b>	MPa	ASTM D 638
Elongation at Break	<b>320</b>	%	ASTM D 638
Shore A Hardness	<b>78</b>	-	ASTM D 2240
<b>Other Standards<sup>[5]</sup></b>			
Modulus at 100% Elongation	<b>10.5</b>	MPa	ASTM D 638

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	<b>1260</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Special Characteristics**

Transparent, Sterilizable, Gamma irradiation sterilization

**Features**

Color Stability

**Certifications**

Medical Grade, US Pharmacopeia Class VI Approved

**Applications**

Medical

**Regional Availability**

North America, Europe