

## 2235L-90 CLEAR 080X

PVC, Flexible

Alphagary

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength	21.4	MPa	ASTM D 638
Elongation at Break	300	%	ASTM D 638
Shore A Hardness	89	-	ASTM D 2240
<b>Other Standards<sup>[S]</sup></b>			
Modulus at 100% Elongation	14.5	MPa	ASTM D 638

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	1270	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Special Characteristics

Transparent, Sterilizable, Gamma irradiation sterilization

#### Applications

Medical

#### Features

Color Stability

#### Regional Availability

North America, Europe

#### Certifications

Medical Grade, US Pharmacopeia Class VI Approved