

7540

PVC, Flexible

Westlake Chemical Corp.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	8.96	MPa	ASTM D 638
Shore A Hardness	54	-	ASTM D 2240
Other properties			
Density	1150	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding, Other Extrusion

Regional Availability

North America

Special Characteristics

U.V. stabilized or stable to weather