

8700

PVC, Flexible

Westlake Chemical Corp.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	11	MPa	ASTM D 638
Shore A Hardness	70	-	ASTM D 2240
Thermal properties			
ASTM Data			
Limiting Oxygen Index	23.5	%	ASTM D 2863
Other properties			
Density	1440	kg/m ³	ASTM D 792

Characteristics**Processing**

Other Extrusion

Regional Availability

North America

Applications

General Purpose