

8750

PVC, Flexible

Westlake Chemical Corp.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	16.2	MPa	ASTM D 638
Shore A Hardness	75	-	ASTM D 2240
Other properties			
Density	1220	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Other Extrusion

Regional Availability

North America

Special Characteristics

Heat stabilized or stable to heat