

Geon™ Vinyl Flexible 83700

PVC, Flexible

GEON Performance Solutions

| Mechanical properties | Value | Unit | Test Standard |
|---------------------------|-------|------|---------------|
| ASTM Data | | | |
| Tensile Strength at Break | 15.2 | MPa | ASTM D 638 |
| Elongation at Break | 320 | % | ASTM D 638 |
| Shore A Hardness | 83 | - | ASTM D 2240 |

| Other properties | Value | Unit | Test Standard |
|------------------|-------|-------------------|---------------|
| Density | 1400 | kg/m ³ | ASTM D 792 |

Characteristics

Delivery form

Pellets

Features

Fungus Resistance

Applications

Automotive, General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa