

Geon™ Vinyl Flexible 90453

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	16	MPa	ASTM D 638
Elongation at Break	340	%	ASTM D 638
Shore A Hardness	82	-	ASTM D 2240
Tear Strength	75.3	kN/m	ASTM D 624

Other properties	Value	Unit	Test Standard
Density	1330	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Other Extrusion

Applications

Automotive

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa