

Geon™ Vinyl Flexible A5DU0

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	20.7	MPa	ASTM D 638
Elongation at Break	340	%	ASTM D 638
Shore A Hardness	90	-	ASTM D 2240
Shore D Hardness	50	-	ASTM D 2240
Tear Strength	118	kN/m	ASTM D 624

Other properties	Value	Unit	Test Standard
Density	1280	kg/m ³	ASTM D 792

Characteristics

Processing

Profile Extrusion

Delivery form

Pellets

Special Characteristics

U.V. stabilized or stable to weather, Transparent

Applications

General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa