

Geon™ Vinyl Flexible A8001

PVC, Flexible

GEON Performance Solutions

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.017	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength at Break	14.5	MPa	ASTM D 638
Elongation at Break	380	%	ASTM D 638
Shore A Hardness	80	-	ASTM D 2240
Tear Strength	57.8	kN/m	ASTM D 624
Compression Set , 22 hr @ 73 °F	25	%	ASTM D 395
Optical properties			
ASTM Data			
Haze	4	%	ASTM D 1003
Light Transmittance	82	%	ASTM D 1003
Other properties			
Density	1200	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Melt temperature	193 - 204	°C	-

Characteristics**Processing**

Injection Molding, Other Extrusion

Delivery form

Pellets

Special Characteristics

Transparent

Applications

General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa