

Geon™ Vinyl Flexible C70T0

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	8.69	MPa	ASTM D 638
Elongation at Break	360	%	ASTM D 638
Shore A Hardness	70	-	ASTM D 2240
Tear Strength	39.2	kN/m	ASTM D 624
Compression Set , 22 hr @ 73 °F	21	%	ASTM D 395

Other properties	Value	Unit	Test Standard
Density	1340	kg/m ³	ASTM D 792

Characteristics

Processing

Other Extrusion

Delivery form

Pellets

Applications

General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa