

## Geon™ Vinyl Flexible C6502

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Break	<b>8.27</b>	MPa	ASTM D 638
Elongation at Break	<b>350</b>	%	ASTM D 638
Shore A Hardness	<b>66</b>	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	<b>1350</b>	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	<b>188 - 199</b>	°C	-

### Characteristics

#### Processing

Injection Molding, Pipe/Tube Extrusion, Other Extrusion

#### Delivery form

Pellets

#### Applications

Building Construction

#### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa