

Geon™ Vinyl Flexible D7500

PVC, Flexible

GEON Performance Solutions

| Mechanical properties | Value | Unit | Test Standard |
|---------------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Tensile Strength at Break | 7.93 | MPa | ASTM D 638 |
| Elongation at Break | 300 | % | ASTM D 638 |
| Shore A Hardness | 75 | - | ASTM D 2240 |
| Tear Strength | 31.5 | kN/m | ASTM D 624 |
| Compression Set , 22 hr @ 73 °F | 30 | % | ASTM D 395 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1480 | kg/m ³ | ASTM D 792 |

Characteristics**Processing**

Other Extrusion

Delivery form

Pellets

Applications

General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa