

Geon™ Vinyl Flexible F78E

PVC, Flexible

GEON Performance Solutions

| Mechanical properties | Value | Unit | Test Standard |
|---------------------------|-------|------|---------------|
| ASTM Data | | | |
| Tensile Strength at Break | 20.7 | MPa | ASTM D 638 |
| Elongation at Break | 200 | % | ASTM D 638 |
| Shore D Hardness | 58 | - | ASTM D 2240 |

| Other properties | Value | Unit | Test Standard |
|------------------|-------|-------------------|---------------|
| Density | 1390 | kg/m ³ | ASTM D 792 |

Characteristics

Processing

Other Extrusion

Delivery form

Pellets

Applications

General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa