

Geon™ Vinyl Flexible F80E

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	15.9	MPa	ASTM D 638
Elongation at Break	300	%	ASTM D 638
Shore A Hardness	78	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1370	kg/m ³	ASTM D 792

Characteristics

Processing

Other Extrusion

Delivery form

Pellets

Features

Melt Strength

Applications

General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa