

Geon™ Vinyl Flexible P1500

PVC, Flexible

GEON Performance Solutions

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	16.5	MPa	ASTM D 638
Elongation at Break	350	%	ASTM D 638
Shore A Hardness	73	-	ASTM D 2240

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Limiting Oxygen Index	24	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1240	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Profile Extrusion, Other Extrusion, Coating

Delivery form

Pellets

Applications

General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa