

MM-PVC E 1580

PVC, Flexible

MACOMASS Verkaufs AG

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	14	MPa	ISO 527
Strain at break	300	%	ISO 527
Shore A hardness	80	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
Density	1200	kg/m ³	ISO 1183

Processing Recommendation Extrusion	Value	Unit	Test Standard
Melt temperature	165 - 175	°C	-
Zone 1	135 - 165	°C	-

Characteristics**Processing**

Other Extrusion

Special Characteristics

Transparent

Additives

Plasticizer

Regional Availability

Europe