

**MM-PVC I 1583**

PVC, Flexible

MACOMASS Verkaufs AG

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Strength	<b>15</b>	MPa	ISO 527
Strain at break	<b>250</b>	%	ISO 527
Shore A hardness	<b>83</b>	-	ISO 7619-1

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1220</b>	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Melt temperature	<b>170</b>	°C	-
Mold temperature	<b>30</b>	°C	-

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

Transparent

**Additives**

Plasticizer

**Regional Availability**

Europe