

POLYVIN PVC 5310

PVC, Flexible

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	5.5	MPa	ASTM D 638
Elongation at Break	250	%	ASTM D 638
Shore A Hardness	50	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1240	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

North America

Applications

Automotive