

2500

PVC

Westlake Chemical Corp.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2910	MPa	ASTM D 638
Tensile Strength at Yield	41.5	MPa	ASTM D 638
Flexural Modulus	2682	MPa	ASTM D 790
Rockwell Hardness	R 110	-	ASTM D 785
Shore D Hardness	78	-	ASTM D 2240
Izod Impact unnotched, 1/8 in	865	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 264 psi	61.8	°C	ASTM D 648
Other properties			
Density	1410	kg/m ³	ASTM D 792

Characteristics**Regional Availability**

North America