

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2827	MPa	ASTM D 638
Tensile Strength at Yield	42.7	MPa	ASTM D 638
Flexural Modulus	2344	MPa	ASTM D 790
Rockwell Hardness	R 110	-	ASTM D 785
Shore D Hardness	80	-	ASTM D 2240
Izod Impact unnotched, 1/8 in	1330	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 264 psi	67	°C	ASTM D 648
Other properties			
Density	1380	kg/m ³	ASTM D 792

Characteristics

Regional Availability

North America