

2602F CLR

PVC

Tekni-Plex

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	45.5	MPa	ASTM D 638
Shore D Hardness	76	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1320	kg/m ³	ASTM D 792

Characteristics**Processing**

Blow Molding

Applications

Packaging

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific

Certifications

Food contact, Food approval FDA 21 CFR