

**5006 Natural**

PVC

Westlake Chemical Corp.

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Modulus	<b>3103</b>	MPa	ASTM D 638
Tensile Strength at Yield	<b>49</b>	MPa	ASTM D 638
Flexural Modulus	<b>3447</b>	MPa	ASTM D 790
Flexural Strength	<b>84.1</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 116</b>	-	ASTM D 785
Shore D Hardness	<b>82</b>	-	ASTM D 2240
Izod Impact notched, 1/8 in	<b>133</b>	J/m	ASTM D 256
Izod Impact notched, 1/4 in	<b>80.1</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-0</b>	-	UL 94
Coefficient of Thermal Expansion, MD	<b>64.8</b>	E-6/K	ASTM D 696
DTUL @ 264 psi	<b>68.9</b>	°C	ASTM D 648

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1330</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Other Extrusion

**Regional Availability**

North America

**Delivery form**

Pellets