

5012

PVC

Tekni-Plex

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	8.96	MPa	ASTM D 638
Modulus at 100% Elongation	2.52	MPa	ASTM D 412
Shore A Hardness	50	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1150	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Applications

Medical