

6300

PVC

Westlake Chemical Corp.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.003	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	3172	MPa	ASTM D 638
Tensile Strength	49.3	MPa	ASTM D 638
Flexural Modulus	2820	MPa	ASTM D 790
Flexural Strength	84.8	MPa	ASTM D 790
Shore D Hardness	83	-	ASTM D 2240
Izod Impact notched, 1/4 in	58.7	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	42.7	J/m	ASTM D 256
Temperature	-20	°C	-

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	74	°C	ASTM D 648
DTUL @ 264 psi	70	°C	ASTM D 648
Limiting Oxygen Index	38	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1400	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Certifications

Drinking water contact, Drinking water contact NSF 61

Chemical Resistance

General Chemical Resistance

Regional Availability

North America