

7900FR

PVC

Tekni-Plex

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	17.9	MPa	ASTM D 638
Modulus at 100% Elongation	8.27	MPa	ASTM D 412
Shore A Hardness	79	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1230	kg/m ³	ASTM D 792

Characteristics**Processing**

Other Extrusion

Applications

General Purpose

Features

Fungus Resistance

Regional Availability

North America, Europe, Asia Pacific