

9175 Amber 12

PVC

Westlake Chemical Corp.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2896	MPa	ASTM D 638
Flexural Strength	89.6	MPa	ASTM D 790
Izod Impact notched, 1/8 in	26.7	J/m	ASTM D 256
Izod Impact notched, 1/4 in	16	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	56	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1330	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Blow Molding

Regional Availability

North America

Applications

Packaging