

9190

PVC

Westlake Chemical Corp.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2992	MPa	ASTM D 638
Flexural Strength	73.4	MPa	ASTM D 790
Izod Impact notched, 1/8 in	1340	J/m	ASTM D 256
Izod Impact notched, 1/4 in	859	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	683	J/m	ASTM D 256
Temperature	0	°C	-

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	61.2	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1310	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

High impact or impact modified

Regional Availability

North America

Applications

Packaging