

9202 J

PVC

Westlake Chemical Corp.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2413	MPa	ASTM D 638
Tensile Strength at Yield	41.4	MPa	ASTM D 638
Flexural Modulus	2241	MPa	ASTM D 790
Flexural Strength	69.6	MPa	ASTM D 790
Izod Impact notched, 1/8 in	1070	J/m	ASTM D 256
Izod Impact notched, 1/4 in	747	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	60	°C	ASTM D 648

Optical properties	Value	Unit	Test Standard
ASTM Data			
Haze	6	%	ASTM D 1003
Light Transmittance	76	%	ASTM D 1003

Other properties	Value	Unit	Test Standard
Density	1290	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

U.V. stabilized or stable to weather

Features

Low Odor

Applications

Packaging

Regional Availability

North America