

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2654	MPa	ASTM D 638
Tensile Strength at Yield	46.9	MPa	ASTM D 638
Flexural Strength	75.8	MPa	ASTM D 790
Rockwell Hardness	R 113	-	ASTM D 785
Izod Impact notched, 1/8 in	801	J/m	ASTM D 256
Izod Impact notched, 1/4 in	133	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	60	°C	ASTM D 648

Optical properties	Value	Unit	Test Standard
ASTM Data			
Haze	4	%	ASTM D 1003
Light Transmittance	84	%	ASTM D 1003

Other properties	Value	Unit	Test Standard
Density	1320	kg/m ³	ASTM D 792

Characteristics

Regional Availability

North America