

Formolon® AWS

PVC

Formosa Plastics Corporation

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2413	MPa	ASTM D 638
Tensile Strength at Yield	41.4	MPa	ASTM D 638
Flexural Modulus	2413	MPa	ASTM D 790
Flexural Strength	68.9	MPa	ASTM D 790
Izod Impact notched, 1/8 in	160	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	71	°C	ASTM D 648

Characteristics**Processing**

Profile Extrusion

Regional Availability

North America

Delivery form

Powder, Natural Color