

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.0035</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Modulus	<b>2790</b>	MPa	ASTM D 638
Tensile Strength at Yield	<b>42.7</b>	MPa	ASTM D 638
Elongation at Break	<b>26</b>	%	ASTM D 638
Flexural Modulus	<b>2620</b>	MPa	ASTM D 790
Flexural Strength	<b>68.9</b>	MPa	ASTM D 790
Shore D Hardness	<b>82</b>	-	ASTM D 2240
Izod Impact notched, 1/8 in	<b>1000</b>	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	<b>590</b>	J/m	ASTM D 256
Temperature	<b>0</b>	°C	-
<b>Thermal properties</b>			
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-0</b>	-	UL 94
DTUL @ 66 psi	<b>70</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>60</b>	°C	ASTM D 648
<b>Other properties</b>			
Density	<b>1360</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Delivery form**

Pellets

**Applications**

Electrical and Electronical

**Special Characteristics**

High impact or impact modified

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa