

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.0035	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Modulus	2380	MPa	ASTM D 638
Tensile Strength at Yield	43.4	MPa	ASTM D 638
Elongation at Break	35	%	ASTM D 638
Flexural Modulus	2480	MPa	ASTM D 790
Flexural Strength	71	MPa	ASTM D 790
Shore D Hardness	79	-	ASTM D 2240
Izod Impact notched, 1/8 in	370	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	110	J/m	ASTM D 256
Temperature	0	°C	-

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 66 psi	72.2	°C	ASTM D 648
DTUL @ 264 psi	68.9	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1330	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	199 - 210	°C	-

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Pellets

**Certifications**

Drinking water contact, Drinking water contact NSF 61

**Applications**

Building Construction, IT / Business Machine, Electrical and Electronical, General Purpose

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa