

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.0035</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Modulus	<b>2960</b>	MPa	ASTM D 638
Tensile Strength at Yield	<b>55.8</b>	MPa	ASTM D 638
Elongation at Break	<b>30</b>	%	ASTM D 638
Flexural Modulus	<b>2960</b>	MPa	ASTM D 790
Flexural Strength	<b>89.6</b>	MPa	ASTM D 790
Shore D Hardness	<b>85</b>	-	ASTM D 2240
Izod Impact notched, 1/8 in	<b>53</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-0</b>	-	UL 94
Thickness tested	<b>1.5</b>	mm	-
DTUL @ 66 psi	<b>68</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>66</b>	°C	ASTM D 648
<b>Optical properties</b>			
<b>ASTM Data</b>			
Haze	<b>8</b>	%	ASTM D 1003
Light Transmittance	<b>70</b>	%	ASTM D 1003
<b>Other properties</b>			
Density	<b>1340</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Delivery form**

Pellets

**Special Characteristics**

Transparent

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa