

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0035	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Modulus	2240	MPa	ASTM D 638
Tensile Strength at Yield	42.1	MPa	ASTM D 638
Elongation at Break	37	%	ASTM D 638
Flexural Modulus	2340	MPa	ASTM D 790
Flexural Strength	66.9	MPa	ASTM D 790
Shore D Hardness	80	-	ASTM D 2240
Izod Impact notched, 1/8 in	960	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	530	J/m	ASTM D 256
Temperature	10	°C	-
Thermal properties			
ASTM Data			
Coefficient of Thermal Expansion, MD	140	E-6/K	ASTM D 696
DTUL @ 66 psi	76.1	°C	ASTM D 648
DTUL @ 264 psi	72.8	°C	ASTM D 648
Other properties			
Density	1260	kg/m ³	ASTM D 792

Characteristics

Delivery form

Pellets

Special Characteristics

High impact or impact modified

Applications

Building Construction, General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa