

GW 2278-LT2-VW1 NAT UV-FG LCF

PVC

Alphagary

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Shore A Hardness	95	-	ASTM D 2240
Tensile Strength	16.5	MPa	ASTM D 412
Elongation at Break	300	%	ASTM D 412

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Limiting Oxygen Index	33	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1400	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Natural Color

Special Characteristics

U.V. stabilized or stable to weather

Features

Fungus Resistance

Applications

Electrical and Electronical

Regional Availability

North America, Europe