

GW 2326-A-VW1 NAT LCF

PVC

Alphagary

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Elongation at Break	400	%	ASTM D 638
Tensile Strength	17.2	MPa	ASTM D 412
Elongation at Break	400	%	ASTM D 412

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Limiting Oxygen Index	28	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1240	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Natural Color

Special Characteristics

Flame retardant

Applications

Electrical and Electronical

Regional Availability

North America, Europe