

**GW 2337-A NATURAL UV-FG LCF**

PVC

Alphagary

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Shore D Hardness	<b>54</b>	-	ASTM D 2240
Tensile Strength	<b>15.9</b>	MPa	ASTM D 412
Elongation at Break	<b>330</b>	%	ASTM D 412

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Limiting Oxygen Index	<b>46</b>	%	ASTM D 2863

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1470</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Delivery form**

Natural Color

**Special Characteristics**

Flame retardant, U.V. stabilized or stable to weather

**Features**

Fungus Resistance

**Applications**

Electrical and Electronical

**Regional Availability**

North America, Europe