

GW 2409-VW1 NAT 50 LCF

PVC

Alphagary

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Shore D Hardness	68	-	ASTM D 2240
Tensile Strength	22.8	MPa	ASTM D 412
Elongation at Break	250	%	ASTM D 412

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Limiting Oxygen Index	29	%	ASTM D 2863

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Volume Resistivity	1E14	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1290	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Natural Color

Regional Availability

North America, Europe